

□ JP05086296

WPIDS  
1992-294070-Full Text

**Reinforcing agents for thermoplastic resins - comprise surface coating with polar gp.  
functionalised polyarylene ether.**

Patent Number EP 501625 A1 2 September, 1992

**Abstract**

EP 501625 A UPAB: 12 November, 1993

Reinforcing agent comprises a glass, ceramic, polymeric or C reinforcing material with a surface coating of a polar-gp.-functionalised polyarylene ether (PAE). Reinforced compsns. comprising 1-75 pts.weight of filler as above and 25-99 pts.weight of thermoplastic resin are also claimed. Reinforcing material pref. comprises with a coating of a sizing compsn., especially an amine, aminosilane or aminophosphine coupling agent. The PAE is pref. poly(2,6-dimethyl-1,4-phenylene) ether, functionalised with a dicarboxylic anhydride, pref. maleic anhydride. Modified PAE is produced by melting a PAE, adding 0.5-15 weight% of maleic anhydride and recovering the resulting prod., and is coated on the reinforcement from a solvent. Resin is pref. a homo- or copolymer of a vinylaromatic monomer, a polycarbonate, polyamide and/or polyarylene ether.

USE/ADVANTAGE - For thermoplastic resins surface coating improves compatibility between the reinforcement and the resin Dwg.0/0

**Inventor(s)**

HUANG, Y; THILL, B P

**Assignee(s)**

(DOWC) DOW CHEM CO

**Application Information**

EP 1992-301065 7 February, 1992

**Priority Information**

US 1991-660461 26 February, 1991  
US 1993-147363 5 November, 1993

**Patent Information**

Number	Kind	Date	Application	Date
(1) EP 501625	A1	2 September, 1992	EP 1992-301065	7 February, 1992
AU 9211239	A	27 August, 1992	AU 1992-11239	25 February, 1992
CA 2061798	A	27 August, 1992	CA 1992-2061798	25 February, 1992
JP 05086296	A	6 April, 1993	JP 1992-79420	18 February, 1992
TW 224981	A	11 June, 1994	TW 1992-101403	25 February, 1992
AU 655627	B	5 January, 1995	AU 1992-11239	25 February, 1992
US 5426171	A	20 June, 1995	US 1991-660461	26 February, 1991
(2) EP 501625	B1	21 August, 1996	EP 1992-301065	7 February, 1992
DE 69212863	E	26 September, 1996	DE 1992-612863	7 February, 1992
KR 206398	B1	1 July, 1999	KR 1992-2771	24 February, 1992
JP 3198465	B2	13 August, 2001	JP 1992-79420	18 February, 1992

(1) - R: AT BE CH DE DK FR GB IT LI NL SE

(2) - R: AT BE CH DE DK FR GB IT LI NL SE



⑪ Publication number : **0 501 625 A1**

⑫

**EUROPEAN PATENT APPLICATION**

⑲ Application number : **92301065.6**

⑤① Int. Cl.<sup>5</sup> : **C08J 5/06, C08J 5/08,**  
**// C08G65/48**

⑳ Date of filing : **07.02.92**

③① Priority : **26.02.91 US 660461**

④③ Date of publication of application :  
**02.09.92 Bulletin 92/36**

⑧④ Designated Contracting States :  
**AT BE CH DE DK FR GB IT LI NL SE**

⑦① Applicant : **THE DOW CHEMICAL COMPANY**  
**2030 Dow Center Abbott Road**  
**Midland, MI 48640 (US)**

⑦② Inventor : **Huang, Yi-Bin**  
**5405 Wallbridge Lane**  
**Midland, Michigan 48640 (US)**  
Inventor : **Thill, Bruce P.**  
**2103 Burlington Drive**  
**Midland, Michigan 48640 (US)**

⑦④ Representative : **Raynor, John et al**  
**W.H. Beck, Greener & Co 7 Stone Buildings**  
**Lincoln's Inn**  
**London WC2A 3SZ (GB)**

⑤④ Reinforcing agents for thermoplastic resins.

⑤⑦ A composition of matter comprising 25 to 99 parts by weight thermoplastic resin and 75 to 1 part by weight solid reinforcing agent having a surface coating of a polar group functionalized polyarylene ether.

**EP 0 501 625 A1**

The present invention relates to reinforcing agents for thermoplastic resins containing additives that have been surface coated with a modifying agent. The surface coating permits improved compatibility between the reinforcing agent and thermoplastic resin.

In Japan Kokai 1-135868, published May 29, 1989, there are disclosed certain resin compositions containing (a) inorganic fillers and (b) polyphenylene ether type resins including maleic anhydride modified poly(2,6-dimethyl-1,4-phenylene) ether. The resins are useful for electrical parts.

According to the present invention there is provided a reinforcing agent for a thermoplastic resin, comprising a glass, ceramic, polymeric or carbon reinforcing material having a surface coating of a polar group functionalized polyarylene ether. The invention also provides a composition of matter comprising A) from 25 to 99 parts by weight of a thermoplastic resin and B) from 75 to 1 parts by weight of such a reinforcing agent.

Polar group functionalized polyarylene ethers are a known class of compounds prepared by contacting polar group containing reactants with polyarylene ethers. The reaction is normally conducted at an elevated temperature preferably in a melt of the polyarylene ether under conditions to obtain homogeneous incorporation of the functionalizing reagent. Suitable temperatures are from 150°C to 300°C. Polyarylene ethers are a known class of polymers having been previously described in United States Patents 3,306,874, 3,306,875, 3,257,357, 3,257,358, and elsewhere. A preferred polyarylene ether is poly(2,6-dimethyl-1,4-phenylene)ether. The polyphenylene ethers are normally prepared by an oxidative coupling reaction of the corresponding bisphenol compound.

Suitable polar groups include the acid anhydrides, acid halides, acid amides, sulfones, oxazolines, epoxies, isocyanates, and amino groups. Preferred polar group containing reactants are compounds having up to 20 carbons containing reactive unsaturation, such as ethylenic or aliphatic ring unsaturation, along with the desired polar group functionality. Particularly preferred polar group containing reactants are dicarboxylic acid anhydrides, most preferably maleic anhydride. Typically the amount of polar group functionalizing reagent employed is from 0.01 percent to 20 percent, preferably from 0.5 to 15 percent, most preferably from 1 to 10 percent by weight based on the weight of polyarylene ether. The reaction may be conducted in the presence of a free radical generator such as an organic peroxide or hydroperoxide agent if desired. Preparation of polar group functionalized polyarylene ethers have been previously described in United States Patents 3,375,228, 4,771,096 and 4,654,405.

The general procedure for obtaining polar group functionalized polyarylene ethers is to contact a reagent containing both ethylenic unsaturation and the desired polar group as previously specified. Generally if less than 0.01 weight percent of the polar group containing reactant is employed, less than desired compatibility between the reinforcing agent and the thermoplastic resin is attained. If greater than 20 weight percent is employed no significant advantage in polymer properties is realized.

The glass, ceramic, polymeric or carbon reinforcing material may be in the shape of fibers having a length to diameter ratio (L/D) less than 5. Preferred particle diameters are from 0.1 micrometers to 1 millimeter. Suitable reinforcing agents include glass microspheres, glass fibers, ceramic whiskers, carbon fiber strands, boron nitride fibers, aramide fibers, etc. Preferred are glass fibers, glass roving or chopped glass fibers having lengths from 0.1 to 10 millimeters and L/D from 5 to 100. One such suitable glass fiber is available from Owens Corning Fiberglas under the designation OCF 414™.

The reinforcing agent may include a sizing agent or similar coating which, among other functions, may promote adhesion between the reinforcing material and the polar group functionalized polyarylene ethers. Suitable sizing agents may contain amine, aminosilane, and aminophosphine functional coupling agents.

Preferred are aminosilane coupling agents such as 3-aminopropyltrimethoxysilane.

Thermoplastic resins suitably utilized in the present invention include homopolymers and copolymers of vinylaromatic monomers, particularly homopolymers and copolymers of styrene. Suitable comonomers include acrylonitrile, methyl methacrylate, N-phenylmaleimide, etc. Preferred copolymers are those containing from 5 to 50 percent by weight of one or more such comonomers. Also included are rubber modified homopolymers and copolymers of vinylaromatic monomers such as high impact polystyrene-containing butadiene or styrene butadiene based elastomers; specifically high impact polystyrene and ABS resins. Preferred vinylaromatic polymers are those having a stereoregular structure that is highly syndiotactic. Additional suitable thermoplastic resins include polycarbonates, polyamides, polyvinylchloride, polyesters, polyimides, and polyarylene ethers. In addition, mixtures of all of the foregoing thermoplastic resins may additionally be employed.

A most preferred thermoplastic resin is syndiotactic polystyrene prepared by coordination polymerization of styrene monomer under conditions to provide a high degree of syndiotacticity. Most highly preferred are those polymers containing greater than 50 percent syndiotacticity at a racemic triad. Such polymers are known in the art having been previously disclosed in United States Patents 4,680,353, 4,959,435, 4,950,724, 4,774,301, and elsewhere.

The compositions of the present invention are prepared by combining the respective components under

conditions to provide uniform dispersal of the reinforcing agent. The surface coating is suitably applied to the reinforcing agent by contacting the same with a solution of the polar group functionalized polyarylene ether. Suitable solvents for dissolving the polar group functionalized polyarylene ether include methylene chloride, trichloromethane, trichloroethylene, trichloroethane, etc. Preferably the concentration of polar group functionalized polyarylene ether in the solution is from 0.1 weight percent to 20 weight percent, preferably 0.5 to 2 percent by weight. After coating of the reinforcing agent the solution is removed such as by evaporation, devolatilization, vacuum drying, etc.

The resulting surface coating is desirably from 0.001 to 10 weight percent of the uncoated reinforcing agent weight. Homogeneous incorporation of the thermoplastic resin and coated reinforcing agent is obtained by mechanical mixing devices such as extruders, ribbon blenders, solution blending or any other suitable technique. Preferred compositions are those containing from 5 to 95 parts thermoplastic resin and 49 to 5 parts reinforcing agent.

Additional additives such as fillers, elastomers, blowing agents, extrusion aids, antioxidants, pigments, plasticizers, stabilizers, lubricants, etc. may also be included in the composition in amounts up to 50 percent, preferably up to 25 percent, by weight.

Having described the invention the following example is provided as further illustrative and is not to be construed as limiting. Unless stated to the contrary parts and percentages are based on weight.

#### Example 1

A maleic anhydride modified polyphenylene oxide resin containing 3 weight percent maleic anhydride (MAPPO) is prepared by injecting maleic anhydride at an appropriate rate to provide the desired maleic anhydride content into a 0.8" (2.0 cm) Welding Engineers Twin Screw extruder which is charged with poly(2,6-dimethyl-1,4-phenylene)ether and operated under conditions to melt plastify the resin. The resulting product is extruded and chopped into granules. A 1 weight percent solution of the resulting MAPPO in trichloroethylene solvent was prepared. Glass fibers (Owens Corning Fiberglas 414™ fiber, desized by treatment with methylene chloride) are contacted with the solution in the following manner. Individual fibers are glued to aluminum tabs using epoxy resin on one end of the fiber. The free fiber end is then dipped into the solution for approximately 1 second, removed and dried in a vacuum oven overnight at approximately 50°C. A molten droplet of the desired thermoplastic resin is picked up on the end of a single fiber applicator and is then transferred, while still molten, to the heated test fiber, by drawing the applicator fiber across the test fiber. Individual adhesive strength measurements on the fibers are then used to quantify the degree of the adhesive strength attained between the resin and the fiber. This technique is referred to as the microbond pullout technique and is disclosed in B. Miller, et al., "A Microbond Method for Determination of the Shear Strength of a Fiber/Resin Interface", Composites Science and Technology, 28, 17-32 (1987).

Comparative runs are performed on individual fibers that are not treated with the maleic anhydride modified polyarylene ether. The identities of the various thermoplastic resins tested and the results of the testing are contained in Table 1. Results are the average of 15 individual fiber tests.

Table 1

Surface Coating	Thermoplastic Resin	Interfacial Shear Strength psi (kPa x 10 <sup>3</sup> )
-	SPS <sup>1</sup>	1700 (12)
MAPPO	SPS	2300 (16)
-	SPS/MAPPO <sup>2</sup>	3500 (24)
MAPPO	SPS/MAPPO	5000 (34)

<sup>1</sup> Syndiotactic polystyrene, Mw 360,000, >95% syndiotactic

<sup>2</sup> Blend of SPS and MAPPO, 2.5 weight percent MAPPO

The above results indicate that improved compatibility between the reinforcing agent and thermoplastic resin is attained by use of the surface coated reinforcing agent of the present invention. This result indicates that resinous blends incorporating the coated reinforcing agents would possess improved compatibility and accordingly improved strength properties, such as tensile and flexural strength.

## Claims

1. A reinforcing agent for a thermoplastic resin, comprising a glass, ceramic, polymeric or carbon reinforcing material having a surface coating of a polar group functionalized polyarylene ether.
2. A reinforcing agent according to Claim 1 wherein the reinforcing material comprises glass fibers.
3. A reinforcing agent according to Claim 1 or Claim 2 which additionally comprises a sizing composition on the surface thereof.
4. A reinforcing agent according to Claim 3 wherein the sizing composition comprises a coupling agent which is an amine, aminosilane or an aminophosphine.
5. A reinforcing agent according to any one of the preceding claims, wherein the polar group functionalized polyarylene ether is a dicarboxylic acid anhydride modified polyarylene ether.
6. A reinforcing agent according to Claim 5 wherein the dicarboxylic acid anhydride modified polyarylene ether is a maleic anhydride modified polyarylene ether.
7. A reinforcing agent according to Claim 6 wherein the maleic anhydride modified polyarylene ether is produced by melting a polyarylene ether, contacting the melted polyarylene ether with from 0.5 to 15 weight percent, based on the polyarylene ether, of maleic anhydride, and recovering the resulting product.
8. A reinforcing agent according to any one of the preceding claims which is prepared by coating the glass, ceramic, polymeric or carbon reinforcing material with a solution of the polar group functionalized polyarylene ether in a solvent and thereafter removing the solvent.
9. A reinforcing agent according to any one of the preceding claims wherein the polyarylene ether is poly(2,6-dimethyl-1,4-phenylene) ether.
10. A reinforced composition comprising from 1 to 75 parts by weight of a filler as claimed in any one of the preceding claims, and from 25 to 99 parts by weight of a thermoplastic resin.
11. A composition according to Claim 10 wherein the thermoplastic resin is a homopolymer or a copolymer of a vinylaromatic monomer, a polycarbonate, a polyamide, a polyarylene ether or a mixture of two or more thereof.
12. A composition according to Claim 11 wherein the thermoplastic resin is syndiotactic polystyrene or a mixture of syndiotactic polystyrene and a polyarylene ether.



European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number

EP 92 30 1065

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.5)
A	US-A-3 881 977 (DAUKSYS R. D.) * claims 1,4-6 *	1,8	C08J5/06 C08J5/08 //C08G65/48
A	GB-A-2 204 888 (TEXTILVER S.A.)  * claims 1,2,11 * * page 3, line 30 - page 4, line 3 * * page 4, line 9 - line 10 * * page 4, line 31 - page 5, line 4 * * page 5, line 12 - line 16 * * page 6, line 8 - line 23 *	1,2,8, 10,11	
A	EP-A-0 260 123 (MITSUBISI GAS CHEMICAL COMPANY INC.) * claims 1,3,6,8 * * page 3, line 22 - line 44 *	1,2,5-7, 9,10	
The present search report has been drawn up for all claims			TECHNICAL FIELDS SEARCHED (Int. Cl.5)  C08J C08G C08F C09D
Place of search THE HAGUE		Date of completion of the search 29 APRIL 1992	Examiner NIAOUNAKIS M.
<b>CATEGORY OF CITED DOCUMENTS</b> X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : number of the same patent family, corresponding document	

EPO FORM 1501 (01.92) (P0401)